

Commercial Solutions Division

3M™ Automotive Window Film

4 mil Obsidian Security Series

Product Bulletin

1. Product Description

4 mil Obsidian Automotive Security films are combined solar and safety window films.

2. Applications

4 mil Obsidian Automotive Security films are intended for interior application on flat to complex curved automotive glazing.

3. Typical Properties

Technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

- Additional impact resistance: The impact strength of a 6 mm tempered glass is 6 to 7 times higher when a 3M 100 µm Obsidian 4 mil security automotive window film is applied to the glass. This was determined according to tests carried out using a modified ANSI Z26.1 Ball Drop Impact Strength test.

These are indicative values for 3M™ Window Film products.

Product construction	
Material base	110 - 130 µm clear or dyed polyester, non-metallized
Adhesive	Pressure sensitive acrylic
Protective liner	Heat shrinkable, siliconized PET

Film Type	Visible Light			Total Solar Energy Rejected (TSER)	G Value (SHGC)	UV Block	Glare Reduction
	Transmission (VLT)	Reflected (exterior)	Reflected (interior)				
	%	%	%	%		%	%
Clear glass (6 mm)	89	9	8	19	81	34	NA
OBS 5 4 mil	7	4	5	45	55	99.9	92
OBS 15 4 mil	19	5	5	41	59	99.8	79
OBS 35 4mil	46	6	6	33	67	99.6	48
OBS 50 4mil	62	7	7	28	72	99.5	30
OBS Clear 4 mil	87	9	9	21	79	99.4	2
Auto glass 75 (6 mm)	73	7	7	42	58	78	NA
OBS 5 4 mil	6	5	4	60	40	99.9	92
OBS 15 4 mil	16	5	5	57	43	99.9	79
OBS 35 4mil	38	6	5	52	48	99.8	50
OBS 50 4mil	51	6	6	48	52	99.8	32
OBS Clear 4 mil	72	7	7	43	57	99.8	4

The values on page 1 are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

4. User Information

4.1 Shelf Life & Storage (prior to application)

Shelf life is 5 years from the manufacturing date. Material should be stored in its original packaging, laying in a horizontal orientation, away from direct sunlight. Heavy objects should not be placed on top of it to avoid damaging the product. Recommended storage conditions are +21°C and 40 – 50% relative humidity. Avoid extreme temperature ranges in storage.

The shelf life as defined above remains an indicative and maximum data, subject to many external and non-controllable factors. It may never be interpreted as warranty.

4.2 Application

These are indicative values for 3M™ Window Film products.

Recommended substrate	Automotive glazing
Recommended surface	Flat to complex curved glazing
Application method	Wet application. Use a heat gun to shrink and fit the film to simple and complex curves when necessary.
Application temperature	From +4°C to +45°C
Service temperature	From -40°C to +70°C
Edge sealing	Not necessary
Drying time	Final adhesion is reached after approximately 15 – 20 days at +18°C and dry conditions. Please refer to local instructions for details.

3M Automotive Window Film is to be professionally applied by skilled, well-trained and 3M authorized installers. Windows can be considered operational after 24 hours.

4.3 Maintenance and Cleaning

Use a cleaning agent designed for high quality glass surfaces. The cleaning agent must be wet and non-abrasive with a pH value between 6 and 8 (neither strongly acidic nor strongly alkaline).

5. Remarks

This bulletin provides technical information only.

To request additional product information see address below.

Important Notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Responsible for this technical bulletin:

3M Deutschland GmbH
Commercial Solutions Laboratory
Carl-Schurz-Str. 1
41453 Neuss, Germany

3M and Scotchgard are trademarks of 3M. All other trademarks are the property of their respective owners.

3M United Kingdom PLC
Commercial Solutions Division
Cain Road
Bracknell, RG12 8HT
UK
www.3m.co.uk/graphics-and-signage-uk/

3M Ireland (Dublin)
The Iveagh Building
The Park, Carrickmines
Dublin 18
Ireland
www.3m.co.uk/graphics-and-signage-uk/

© 3M 2020. All rights reserved.