

Data sheet

Product: **AE 7150 AE 7151 - Adeletr CG 150**

Film **Plastified calandered PVC Phthalat free**

Thickness:

Dimensional Stability:

Color:

Finish:

U.M.	Method	Typical value (Average val.)
my	measur.	ca. 150
%	(5' - 70 °C)	<= 3
		Transp.
		Gloss

Liner **Glass Kote**

Weight:

Color:

U.M.	Method	Typical value (Average val.)
gr/mq	measur.	ca. 200
		White

Surface tension

34 dynes/cm +/- 2

Shrinkage 1 min. at 21 ° C after separation from liner

U.M.	Method	Typical value (Average val.)
mm	measur.	CD < 2%
mm	measur.	MD < 4%

Certifications

This film do not contain phtalat in its plasticizer; it is produced in respecting of European guideline 1999/781/EC and 2004/781/EC for applications such as children's toy. However, it is not always possible to preclude low level raw material.

Usage

Ink-Jet Solvent / Ecosolvent

UV Ink-Jet, Latex

The material must not come in contact with sources of heat and or of damp.

Have the product, closed in his packing, for at least 24 hours acclimatized before the use.

One advises to execute print tests to verify the compatibility of the used inks.

Usage temperature 20 ° C approx.

Storage

The material must be stored in environment with a temperature of 20 ° C and 55 % relative umidity ap.

One advises not to keep the material in stock for periods higher than nine months.

Shelf liife

Stored at 15 - 25 ° C nine month

Utilization

The Adeletr can be applied on avery glass-smoth surface like glass, plastic, pre-painted plate etc.

Before the application it is essential to clean the interested surface, preferably with a cloth damp, removing every dust track, greasy or fat.

Min. applying temperature 5 ° C (41° F) minimum

Disposal

PVC films are considered as special industrial, not dangerous, waste; it can be disposed like urban solid waste.

GENERAL REMARK:

- Labels or sticker have not to be applied onto dusty, dirty, oily or oroxidized surface
- Mould release agents on blow-moulded plastic surface inhibit adhesion
- Do not use Adeletr outside the recommended temperature range, or do not apply below the minimum application temperature
- Adhesion failure may occur on substrated with low surface tension
- Adeletr mast to be applied to clean and dry surface, free from any contamination

All statements, technical information and recommendations about Adex products are based upon tests believed to be reliable and show typical average measures, but donq constitute a guarantee or warranty.

All Adex products are sold with the understanding that PURCHASER has independently determined the suitability of such products for its purposes.

Adex srl

Via Segrino, 10

20098 San Giuliano M.se fraz. Sesto Ulteriano

CCIAA P.IVA 04396250963

Tel. ++39 (0)2 98280949

Fax. ++39 (0)2 98280408

Email: info@adexsrl.it