

► DPF 6000RP White

Premium Cast Digital Print Pressure-Sensitive Vinyl Film

DPF 6000RP White is a 2-mil (50 microns) gloss cast film with tinted, clean removing, high tack, permanent pressure-sensitive adhesive. Designed for large format graphics, DPF 6000RP White is made of premium quality cast facestock with a special lay-flat liner. The special adhesive system is designed to provide excellent opacity, as well as easy installation. The film provides superior conformability around rivets, curves, contours and channels. DPF 6000RP White is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Digital printing with a wide variety of direct print systems
- Fleet and vehicle applications, Window Graphics, Wall Graphics (Interior), Multipurpose Commercial
- Warrantied for use on rivets, corrugations and channel structures*
- Used in conjunction with Series 3200, Series 3210, Series 3220, Series 3270 or Series 33505 overlaminates
- Certified for Europe Rail External Application in Combination with Series 3350

**Channel applications should be installed using Arlon's approved installation methods found at www.arlon.com and www.wrapitright.com.*

DPF 6000RP and Series 3350 are not warrantied around compound curves

**Certified for
HP Latex Inks**

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss)
THICKNESS	Micrometer, Federal Bench Type	2-mil (50 micron)
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 1.25 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 150%
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment
APPLICATION TEMPERATURE RANGE	On clean, dry substrate (flat)	4.4°C to 38°C
	On clean, dry substrate (corrugated with rivets and channels)	15°C to 38°C optimum
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°C to 79°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.38 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 0.45 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	12 g/cm

NOTE: Recommended post-heat surface temperature of vinyl installed: 203°F to 221°F (95°C to 105°C). Post-heat must be applied gradually and approximately 13 cm from the film in order to avoid the matte from turning glossy. The recommended post-heat temperature applies to the media & matte overlaminate wrap. Standard Terms & Conditions Apply

USA

- a** 200 Boysenberry Lane, Placentia, CA 92870
- p** 800 232 7161 / +1 714 985 6300
- f** +1 714 985 6305

EUROPE

- a** Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
- p** +31 70 354 4311
- f** +31 70 355 7721

CHINA

- a** No. 1989 Xinchang Road, Weifang, Shandong, 262400
- p** +86 0536 6226568

RAIL EXTERNAL APPLICATION

DPF 6000RP White is certified for Europe overland rail external application in combination with Series 3350 overlamine, in accordance with BS 6853 1999 Annex D8.4 & BS 476 Part 7:

TEST METHOD	RESULT	Acceptability Criteria
		Cat Ib
FLAME SPREAD	Class 1 (nil spread)	Class 1
SMOKE EMISSION	A0(ON) = 5.82	A0(ON) < 7.0
	A0(OFF) = 6.22	A0(OFF) < 10.5
TOXIC FUME EMISSION	R = 0.054	R < 2.7

OPTIMUM PERFORMANCE

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility. DPF 6000RP White will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as high deposition of dirt and atmospheric contaminants. Arlon does not recommend its film for horizontal or close horizontal applications. Use heat and/or chemical when removing image from vehicle (see Installer Handbook for details).




TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:




All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

April 2020



USA

 200 Boysenberry Lane, Placentia, CA 92870
 800 232 7161 / +1 714 985 6300
 +1 714 985 6305

EUROPE

 Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 +31 70 354 4311
 +31 70 355 7721

CHINA

 No. 1989 Xinchang Road, Weifang, Shandong, 262400
 +86 0536 6226568

arlon.com